

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representation of
The original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**

THIS PAGE BLANK (USPTO)



Europäisches Patentamt
European Patent Office
Office européen des brevets

Publication number:

**0 401 044
A2**

12

EUROPEAN PATENT APPLICATION

21 Application number: 90306019.2

51 Int. Cl. 5: **C08J 3/24, C08J 3/12,
//C08L101:02**

22 Date of filing: 01.06.90

30 Priority: 01.06.89 GB 8912600

43 Date of publication of application:
05.12.90 Bulletin 90/49

64 Designated Contracting States:
DE DK ES FR GB IT NL SE

71 Applicant: **ALLIED COLLOIDS LIMITED**
P.O. Box 38 Low Moor
Bradford West Yorkshire, BD12 0JZ(GB)

72 Inventor: **Johnson, Ian Michael**
6 Amport Close
Brighouse, West Yorkshire(GB)

74 Representative: **Lawrence, Peter Robin**
Broughton et al
GILL JENNINGS & EVERY 53-64 Chancery
Lane
London WC2A 1HN(GB)

54 Absorbent polymers and their production.

57 Fines or other particles of water swellable polymeric material are converted into a gel mass by absorbing an aqueous solution of a cross linking agent into the fines, cross linking occurs between the cross linking agent and pendant groups in the polymer, and the mass is dried and comminuted. The polymer is preferably a cross linked sodium acrylate polymer and the cross linking agent is preferably a glycidyl ether or a silane cross linking agent. The product is novel and comprises a polymer structure that is formed of zones in which the polymer is substantially free of cross links between pendant groups, and the zones are interconnected by cross links through the pendant groups.

EP 0 401 044 A2

Absorbent Polymers and their Production

Absorbent polymers are widely made in the form of water insoluble, water swellable, particulate polymeric material derived by polymerisation of water soluble polymerisable material in the presence of a cross linking agent. The cross linking agent is usually a polyethylenically unsaturated monomer, which thus causes cross linking in the backbone of the polymer. However it is known also to cross link through pendant groups, for instance by reaction of pendant carboxylic groups with an aluminium or other polyvalent metal compound.

The particulate material is generally made by reverse phase bead polymerisation followed by drying and separation of the beads, or by bulk gel polymerisation followed by drying and comminution. These processes generally provide a product having a spread of particle sizes and in particular a product containing a fraction of particle size that is smaller than is desirable having regard to, for instance, flowability and the risk of environmental problems due to dusting. Generally this fraction of "fines" is separated from the particulate material. Its upper particles size will be selected according to the processing conditions. It may be as high as 150 or 200 μ m or as low as 50 μ m or even lower.

The separated fines cannot usually be used as such and so they are usually either dumped or put back into a wet stage in the process so that their polymeric material forms a part of the final dried particulate material. Unfortunately the recycling of fines in this manner tends to reduce the gel strength of the final particulate material.

Important properties for such material include gel strength, gel capacity, and rate of water absorption. Increasing degrees of cross linking tend to increase the gel strength but decrease the gel capacity and so the cross linking has to be optimised to obtain the optimum combination of gel strength and gel capacity. It is therefore very undesirable to cause an unwanted reduction in gel strength.

It is known that the rate of water absorption can be increased by reacting the surfaces of the particles with a cross linking agent, so as to form a relatively highly cross linked surface layer. Typically the cross linking agent is a polyvalent metal compound that reacts with carboxylic groups in the polymer molecules close to the surface of the particles.

In EP 195406 the preformed polymer is reacted in the presence of water with a silane coupling agent. It is stated that this can be performed by adding a mixture of water and the silane coupling agent to the water absorbing polymer in the dried state and heating the resulting mixture to evaporate

water. It appears that, in all the relevant examples, the reaction was conducted while the polymer was dispersed in a non-aqueous liquid with the result that the polymer substantially maintains its initial particulate state throughout the reaction with silane.

Although this process may be a useful way of improving the rate of water absorption, and possibly also the gel strength, of preformed particles of a satisfactory size, it is of no assistance in the problem of dealing with particles that are too small.

According to the invention, water insoluble, water swellable, particulate polymeric material is made from dry particles of a water-swellable polymer formed from water-soluble ethylenically unsaturated material, by a process comprising forming a gel mass by a process comprising absorbing an aqueous solution of a cross-linking agent into the said dry particles, causing cross linking of the polymer in the gel mass by reaction between the cross-linking agent and pendant groups in the polymer, and drying and comminuting the gel mass.

Thus in the invention we form dry particles of water swellable polymer and then convert them back into a gel mass in which they become cross linked, and the mass is then recomminuted and redried. This is entirely different from processes of surface cross linking, such as EP 195406, since in such processes the particles that are treated with the cross linking agent do broadly retain their original configuration throughout the process. In the invention however the fines become an integral part of the gel mass and thus permanently lose their particulate form within that mass.

The dry particles that are used to form the gel mass preferably have a substantial proportion of fine particles in them. Generally at least 30%, and often at least 50%, may be fines, for instance below 200 μ m and usually below 150 μ m, preferably below 100 μ m. Particles below 50 μ m can cause particularly serious dusting problems and so the invention is of particular value when applied to a fraction having at least 50%, and sometimes at least 90% by weight below 50 μ m.

The initial particles can be a fraction sieved from a product, in which event at least 90% of the particles will generally be below 200 and usually below 150 μ m, usually below 100 μ m.

The invention is, however, also of value for upgrading the quality of a particulate product that does contain particles of a satisfactory size above 200 μ m but also contains an unacceptably large proportion of fines. Thus the dry particulate product that is formed into the gel mass can be a product which is 0 to 70% by weight, often 0 to 50% by

weight, above a chosen particle size and 30 to 100%, often 50 to 100% by weight below that particle size, generally 200 μ m or 150 μ m, most preferably 100 μ m.

The dry particles may have been made by reverse phase bead polymerisation, generally followed by sieving to produce a fines fraction for use in the invention, but more usually is made by a process comprising drying and comminution of larger particles. These larger particles may have been made by reverse phase bead polymerisation but, more usually, are made by comminution of gel made by bulk gel polymerisation.

The polymer in these particles can be linear but is generally a cross linked polymer. Usually it is a polymer formed from water soluble ethylenically unsaturated material comprising polyethylenically unsaturated cross linking agent with the result that the polymer is cross linked in the backbone of the polymer. The water soluble ethylenically unsaturated material may be a single water soluble ethylenically unsaturated monomer or may be a water soluble blend of ethylenically unsaturated monomers.

The ethylenically unsaturated material can be non-ionic, anionic or cationic. If it is ionic, it can be a blend of non-ionic and ionic monomers, the amount of non-ionic monomer often being 0 to 90%, and usually 0 to 70%, by weight of the blend.

The preferred ethylenically unsaturated material is generally anionic and may be formed from anionic monomer alone or a blend of anionic and non-ionic monomers. Although sulphonic monomers (e.g., allyl sulphonate or 2-acrylamido-2-methyl propane sulphonate) can form part of the anionic monomer, it is generally preferred that the ethylenically unsaturated material should comprise carboxylic monomer, for instance methacrylic acid, maleic acid, itaconic acid, crotonic acid or, preferably, acrylic acid.

Suitable non-ionic monomers include vinyl pyrrolidone, methacrylamide or, preferably, acrylamide.

Suitable cationic monomers include dialkylaminoalkyl (meth) -acrylamides and -acrylates, usually as acid addition or quaternary salts. Examples are dimethylaminoethyl (meth) acrylates and dimethylaminopropyl (meth) acrylamides.

Preferred polymers are formed from 10 to 100%, often 30 to 100%, acrylic acid with the balance being acrylamide. The acrylic acid can be entirely in the form of free acid but, provided this does not interfere with the cross linking reaction, at least 50% and usually at least 75% of the acid groups are present in the form of sodium or other alkali metal or other water soluble salt.

The dry particles will often have conventional dryness as a result of drying followed by exposure

to the ambient atmosphere, for instance below 15% moisture, and so the process can be applied to the treatment of previously made product. However the process of the invention can also be conducted as part of the overall production process starting with polymerisation of the monomer or monomer blend and then the dry particles do not have to be dried fully before they are rewetted and can, instead, still be slightly moist, for instance having a moisture content up to 20 or 25%. They must however be sufficiently dry that they behave primarily as fully dried particles rather than as sticky particles.

The particles are then mixed with sufficient of an aqueous solution of a cross linking agent to form a gel mass. Depending upon the degree of cross linking in the initial particles the total amount of water at this stage will usually be at least 20% (by weight based on the weight of particles and added aqueous solution). Although 20% may be adequate if the polymer particles were linear the amount is usually at least 30% by weight, especially when the starting polymer is cross linked. It is undesirable to add too much water at this stage since it has to be removed subsequently and so generally the total amount of water at this stage is preferably below 70%, most preferably below 60%. Water content of around 50% is generally preferred.

In addition to converting the individual particles back to a gel mass, the aqueous solution must also carry the cross linking agent into the gel mass. This cross linking agent may penetrate uniformly throughout the particles or may be concentrated primarily at what were, originally, the interfaces of adjacent particles.

Thus a preferred novel product according to the invention is a water insoluble, water swellable, particulate polymeric material formed from ethylenically unsaturated material wherein the polymeric material has a polymer structure that is formed of zones in which the polymer is substantially free of cross links between pendant groups in the polymer and the zones are interconnected by cross linking through pendant groups in the polymer. Each zone generally corresponds to one of the initial dry particles in which the polymer structure is either linear, if the starting particles were linear, or more usually is cross linked in the backbone by a polyethylenically unsaturated monomer.


The cross linking agent is one that will react with pendant groups in the polymer before or during the final drying so as to cause cross linking. Preferably the cross linking agent reacts with carboxylic groups in the polymer and so preferably the polymer is anionic. However it is possible to cross link through other pendant groups, and such groups can be included primarily for the purpose of providing a cross linking function in the polymer.

The cross linking agent must be selected such that it is capable of reacting with the chosen groups.

The use of a polyvalent metal compound, such as a compound of aluminium can be suitable when the groups are carboxylic and the polymer is linear, and will lead to ionic cross linking. However this cross linking is usually inadequate when the polymer is swellable (and cross linked) rather than soluble because it may not resist adequately the swelling forces that exist within the final particles when they swell.

Preferably therefore the compound is one that leads to covalent cross linking, in which event the cross linking agent should be a compound that has at least two functionalities capable of reacting with carboxylic or other pendant groups. Suitable functionalities include hydroxy and epoxide groups and thus suitable compounds include glycidyl ethers and polyepoxy compounds such as ethylene (or polyethylene) glycol diglycidyl ether, glycerol (or diglycerol or polyglycerol) polyglycidyl ether and sorbitol polyglycidyl ether and polyhydroxy compounds such as ethylene glycol, glycerol and trimethylol propane.

A preferred cross linking agent is a silane coupling agent, and the materials described in detail in EP 195406 are suitable. Such materials can have the formula



wherein X represents a group having a functional group capable of reacting with the carboxyl group and/or the carboxylate group of the water-absorbing polymer, R represents a hydrocarbon group, Y represents a hydrolyzable group, and m is 0, 1 or 2.

In formula (1), X is a group having a functional group capable of reacting with the carboxyl group and/or the carboxylate group of the water-absorbing polymer. Examples include an epoxy group, an amino group, a mercapto group, a chlorine atom and a carbon of a quaternary amine.

Y is a hydrolyzable group such as a lower alkoxy group or a lower acyloxy group. Preferably, these groups have 1 to 4 carbon atoms. It is believed that the hydrolyzable group undergoes hydrolysis to form a silanol group which is dehydrocondensed in a well known manner to form an Si-O-Si bond.

R is a hydrocarbon group, for example, an alkyl or aryl group, preferably an alkyl group having 1 to 4 carbon atoms or a phenyl group.

m is 0, 1 or 2. In other words, the silane coupling agent of formula (1) should have the hydrolyzable group (Y) as an essential group, but does not always have to contain the hydrocarbon group (R).

Examples of the silane coupling agents of formula (1) are gamma-gly-

cidoxypropyltrimethoxysilane, gamma-glycidoxypolydimethyldiethoxysilane, beta-(3,4-epoxycyclohexyl)ethyltrimethoxysilane, gamma-(2-aminoethyl)-aminopropyltrimethoxysilane, gamma-(2-aminoethyl)-aminopropylmethyldimethoxysilane, gamma-aminopropyltriethoxysilane, N-phenylgamma-aminopropyltrimethoxysilane, gamma-mercaptopropyltrimethoxysilane, gamma-mercaptopropylmethyldimethoxysilane, gamma-chloropropyltrimethoxysilane, gamma-chloropropylmethyldimethoxysilane and octadecyldimethyl[3-(trimethoxysilyl)propyl]ammonium chloride. Of these, silane coupling agents having a glycidyl group as the functional group X, such as gamma-glycidoxypropyltrimethoxysilane, are preferred.

The concentration of cross linking agent in the aqueous solution is selected having regard to the level of cross linking that is required and the amount of solution that is being absorbed into the particles. Generally the dry weight of cross linking agent is within the range 0.05 to 5%, most usually 0.1 to 1%, dry weight based on the dry weight of polymer.

The cross linking reaction may occur relatively spontaneously upon absorption of the aqueous solution into the dry particles or, depending upon the choice of cross linking agent, it may be necessary to maintain the gel mass at ambient or elevated temperature for a suitable period to allow cross linking to occur or it may be necessary to heat the gel mass. Often any heating that is required can be provided during the drying and so a convenient process comprises absorbing the aqueous solution into the dry particles to form a gel mass and substantially immediately drying the mass by heating and comminuting the mass. In order to ensure uniform distribution of the aqueous solution, it is generally necessary to stir the particles and gel mass, for instance by a screw mixer, during the absorption. The mass may be comminuted into large pieces prior to or during the drying in conventional manner and is generally comminuted to the desired final particle size prior to final drying on, for instance, a fluidised bed in conventional manner.

The final particle size can be selected by appropriate choice of drying and comminution conditions in conventional manner and is usually below 2mm, preferably below 1mm. At least 90% of the particles are preferably above 200µm and if any significant proportion of fines are produced it can be convenient to sieve these out and recycle them again. The average particle size of the final particles is usually at least twice the average particle size of the initial particles. The amount of particles below 200µm in the final product is usually below half, and often below quarter, of the amount in the initial dry particles.

The resultant particles may be used by themselves or they may be used blended with particles that have not been subjected to the process. For instance a conventional process for making absorbent polymer particles may be modified by separating the fines from that process, treating the fines in accordance with the invention and then recombining the resultant treated particles with the main production.

In another process, the aqueous solution of cross linking agent is absorbed into the dry particles and subsequently or simultaneously the gel mass is formed by blending the product of this absorption with the main production of water absorbent polymer, i.e., the product of the gel polymerisation.

Typical amounts of cross linked fines that may be incorporated back into the gel or mixed with dried product are in the range 5 to 50%, often 5 to 20%, based on the total weight of polymer.

The final product, either consisting solely of the treated fines or these blended with other absorbent polymer, can be used in any situation where absorbent polymer is conventionally used but is of particular value for absorbing water from particulate masses for instance as in EP 195550 or GB 2,200,133. The final product has improved gel strength whilst retaining satisfactory gel capacity.

The following are examples.

Example 1

100kg of water containing 0.5Kg of 3-glycidylpropyl-trimethoxysilene (glymo) are mixed in a scroll mixer with 100kg of a dry cross linked sodium polyacrylate powder with a particle size less than 100 microns sieved from a conventional product made by gel polymerisation and drying and comminution. Both components are added continuously at such a rate as to produce a reconstituted gel at 50% solids. The resultant gel is cut into small pieces prior to drying in a fluid bed drier at 100°C. The coarse dry powder is ground and the product between 850 and 900µm retained.

The process is prepared using the same techniques, but omitting the glymo; for use as a control.

On swelling in water or saline solution the product made using the glymo is able to maintain a firm structure in the swollen state. The control polymer reverts back to swollen fines which are quite soft.

Example 2

The gel strength at different levels of torque is measured on various products. Product A is made

by adding an aqueous liquor to a dry particulate material from which the fines used in Example 1 have been obtained by sieving.

In product B, the gel mass is obtained from the same particulate material as in product A except that 10% of the fines described in Example 1 (without treatment with glymo) are recycled to the gel in conventional manner.

Product C is the same as product B except that the fines are treated with glymo in accordance with Example 1 before the recycling.

The gel strength of product C is considerably greater, especially at high torque values, than the gel strength of product A which, in turn, is greater than the gel strength of product B.

Example 3

50 grams of cross linked sodium polyacrylate fines are added into a food processor and mixed at slow speed. Sufficient aqueous solution is added to cause the fines to agglomerate into a gel and the speed is then increased to break down any large agglomerates. The product is dried in an oven at 80°C and sieved between 850µm and 45µm. The resultant particles are then tested for their capacity and rate of absorption of 0.9% aqueous sodium chloride. The amount of cross linking agent that is provided by the solution ranged from 0.5% to 1.5%, and the cross linking agent was ethylene glycol diglycidyl ether. The drying temperatures range from 80 to 110°C. The absorption capacities were all very satisfactory. The rate of uptake is greatest using 1.5% of the cross linking agent. The optimum amount of glycidyl ether or other cross linking agent will therefore be selected having regard to the particular balance of absorption properties that are required and in some instances, especially when using materials such as glycidyl ethers, optimum amounts range up to 3%, 5% or even up to 10%.

Claims

1. A process of making water insoluble, water swellable, particulate polymeric material from dry particles of a water swellable polymer formed from water soluble ethylenically unsaturated material and which comprises forming a gel mass by absorbing aqueous solution of cross linking agent into the said dry particles, causing cross linking of the polymer in the gel mass by reaction between the cross linking agent and pendant groups in the polymer, and drying and comminuting the gel mass.

2. A process according to claim 1 in which the

said dry particles are formed from water soluble ethylenically unsaturated material comprising polyethylenically unsaturated cross linking agent and are swellable, water insoluble, particles and have a gel capacity of at least 20g deionised water per gram polymer.

3. A process according to claim 2 in which the dry particles have a moisture content of up to 20% and the amount of water introduced by the aqueous solution is from 30 to 70% by weight based on the weight of particles and added aqueous solution.

4. A process according to claim 2 in which the polymer particles are anionic, water swellable, water insoluble particles.

5. A process according to claim 2 in which the polymer particles are formed from 30 to 100% acrylic acid or water soluble salt thereof with 0 to 70% acrylamide and are cross linked, water insoluble, water swellable particles.

6. A process according to claim 2 in which the cross linking agent is a covalent cross linking agent that will react covalently with pendant groups in the polymer.

7. A process according to any preceding claim in which the polymer is anionic and contains carboxylic groups and the cross linking agent is selected from silane coupling agents and materials providing at least two groups selected from hydroxyl and epoxide groups.

8. A process according to any preceding claim in which the polymer is an anionic polymer containing carboxyl groups and the cross linking agent is selected from silane coupling agents and glycidyl ethers.

9. A process according to any preceding claim comprising absorbing the said aqueous solution into the said dry particles and subsequently or simultaneously blending the product of this absorption by a polymer gel made by gel polymerisation.

10. A process according to any preceding claim in which the dry particles are made by sieving fines from a product made by reverse phase bead polymerisation or from a product made by drying and comminuting gel particles made either by reverse phase bead polymerisation or by comminution of gel made by bulk gel polymerisation.

11. A process according to claim 10 in which at least 90% by weight of the fines have a particle size below 100µm.

12. A water insoluble, water swellable, particulate polymeric material formed from ethylenically unsaturated material, wherein the polymeric material has a polymer structure that is formed of zones in which the polymer is substantially free of cross links between pendant groups in the polymer and the zones are interconnected by cross links through pendant groups in the polymer.

13. A polymeric material according to claim 12

in which the polymer has carboxylic pendant groups and has a cross linked polymeric backbone, and the cross links are provided by a covalent cross linking agent.

14. A polymer according to claim 12 formed from 30 to 100% acrylic acid as free acid or water soluble salt and 0 to 70% acrylamide and in which the cross links are provided by a glycidyl ether or silane coupling agent.

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) Publication number:

0 401 044 A3

(12)

EUROPEAN PATENT APPLICATION

(21) Application number: 90306019.2

(51) Int. Cl.⁵: **C08J 3/24**, **C08J 3/12**,
//**C08L101:02**

(22) Date of filing: 01.06.90

(30) Priority: 01.06.89 GB 8912600

(43) Date of publication of application:
05.12.90 Bulletin 90/49

(64) Designated Contracting States:
DE DK ES FR GB IT NL SE

(68) Date of deferred publication of the search report:
13.11.91 Bulletin 91/46

(71) Applicant: **ALLIED COLLOIDS LIMITED**
P.O. Box 38 Low Moor
Bradford West Yorkshire, BD12 0JZ(GB)

(72) Inventor: **Johnson, Ian Michael**
6 Amport Close
Brighouse, West Yorkshire(GB)

(74) Representative: **Lawrence, Peter Robin**
Broughton et al
GILL JENNINGS & EVERY 53-64 Chancery
Lane
London WC2A 1HN(GB)

(54) **Absorbent polymers and their production.**

(57) Fines or other particles of water swellable polymeric material are converted into a gel mass by absorbing an aqueous solution of a cross linking agent into the fines, cross linking occurs between the cross linking agent and pendant groups in the polymer, and the mass is dried and comminuted. The polymer is preferably a cross linked sodium acrylate polymer and the cross linking agent is preferably a glycidyl ether or a silane cross linking agent. The product is novel and comprises a polymer structure that is formed of zones in which the polymer is substantially free of cross links between pendant groups, and the zones are interconnected by cross links through the pendant groups.

EP 0 401 044 A3



European
Patent Office

EUROPEAN SEARCH REPORT

Application Number

EP 90 30 6019

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl.5)
X	GB-A-2 126 591 (KAO CORP.) * Claims 1,4,5; page 1, line 23 - page 2, line 12; page 3, lines 10-37; examples 6,13 *	1-8,12-14	C 08 J 3/24 C 08 J 3/12 // C 08 L 101:02
Y	-----	1-8,10-14	
Y	EP-A-0 277 017 (ALLIED COLLOIDS LTD) * Claims 1,17,18; page 4, lines 41-64; page 5, lines 8-26; page 5, lines 36-42; page 5, line 55 - page 6, line 10; example 10 * & GB-A-2 200 133 (Cat. D) -----	1-8,10-14	
			TECHNICAL FIELDS SEARCHED (Int. Cl.5)
			C 08 J
The present search report has been drawn up for all claims			
Place of search The Hague		Date of completion of search 14 August 91	Examiner HALLEMEESCH A.D.
<div>CATEGORY OF CITED DOCUMENTS</div> <div>X: particularly relevant if taken alone Y: particularly relevant if combined with another document of the same category A: technological background O: non-written disclosure P: intermediate document T: theory or principle underlying the invention</div> <div>E: earlier patent document, but published on, or after the filing date D: document cited in the application L: document cited for other reasons ----- &: member of the same patent family, corresponding document</div>			